


## 850390 (CFRP)



Material Group	$v_c$ (m/min)	$f_n$ (mm/rev)													
		ø1.0 -1.9	ø2.0 -2.9	ø3.0 -3.9	ø4.0 -4.9	ø5.0 -5.9	ø6.0 -6.9	ø7.0 -7.9	ø8.0 -9.9	ø10.0 -11.9	ø12.0 -13.5	ø14.0 -15.5	ø16.0 -17.5	ø18.0 -19.5	ø20.0
 83	<b>125</b> (100-150)	-	0.03	0.04	0.04	0.05	0.05	0.06	0.06	0.07	0.07	-	-	-	-

 $v_c$  - cutting speed (m/min) $n$  - RPM (rev/min) $f_n$  - feed rate (mm/rev) $\phi$  - drill diameter (mm)To calculate RPM from cutting speed:  $n = \frac{v_c \cdot 1000}{\pi \cdot \phi}$ To calculate cutting speed from RPM:  $v_c = \frac{n \cdot \pi \cdot \phi}{1000}$ 

All recommendations are based on ideal machining conditions. Adjustments may need to be made according to your set-up. The recommendations for speeds, feeds and other parameters presented in this chart are nominal recommendations and should be considered only as good starting points.